

THE BEST JUST GOT BETTER!

THE ORIGINAL SINCE 1931

SIL•FOS® COILS

SIL•FOS® 15 is the preferred alloy for general copper-copper brazing in the **SIL•FOS®** family. For copper-to-copper joints the phosphorus in the **SIL•FOS®** product serves as the fluxing agent and no separate flux is necessary. For brass applications however, flux is recommended. For use where close fit-ups cannot be maintained **SIL•FOS® 15** works well to “bridge” gaps. Highest joint ductility of the entire **SIL•FOS®** family to best withstand the stresses inherent in refrigeration applications. **SIL•FOS® 5** is a lower silver alternative with the ability to fill gaps and form fillets.

Each coil of alloy is marked with the Lucas-Milhaupt product name and alloy designation.



Product Name	AWS Spec	Compositions %			Melt		Flow	
		Ag	Cu	P	°F	°C	°F	°C
SIL•FOS® 15	BCuP-5	15	80	5	1190	643	1475	802
SIL•FOS® 5	BCuP-3	5	89	6	1190	643	1495	813

Product Name	P/N	Description
SIL•FOS® 15 Coil	32181	.050" x .125" x 5' length
	32182	.050" x .125" x 10' length
	32183	.050" x .125" x 22' length
SIL•FOS® 5 Coil	32299	.050" x .125" x 5' length
	32301	.050" x .125" x 10' length
	32302	.050" x .125" x 22' length



Lucas-Milhaupt, Inc.
A Handy & Harman Company
Milwaukee, WI 53110
www.silfos.com