

## Handy Flux<sup>®</sup> Liquid

### ***GENERAL DESCRIPTION***

---

Handy Flux Liquid is a liquid active fluoride/borate-type flux in paste form, which has been specially formulated for us in jewelry industry or brazing of small parts and assemblies. This product is often used in atmosphere furnace brazing where the atmosphere is not of good quality to promote satisfactory wetting of the assemblies by the braze filler metal. It is recommended to use with filler metals that flow between 1100°F (593°C) - 1600°F (871°C).

### ***PRODUCT APPLICATION***

---

Handy Flux Liquid is primarily used as a general purpose brazing flux in brazing applications involving brazing of steel, stainless steel, copper, copper alloys, nickel, and nickel alloys. It is not recommended to use in aluminum bronze or other aluminum alloy brazing applications. Handy Flux Liquid is suitable for use with most heating methods including torch, induction or furnace.

### ***POST CLEANING***

---

This product is corrosive and a post braze cleaning or rinsing operation is required. The flux residue is easily dissolved in hot water at temperatures of 120°F (49°C) or higher.

### ***WARRANTY & STORAGE***

---

Lucas-Milhaupt, Inc. warrants their Water Based Fluxes for twelve months from the date of shipment if stored in the original, unopened container. Optimal storage conditions would be 65°F (18°C) - 75°F (24°C), cool and dry.

Twelve months should not be interpreted as the shelf or useful life of the product unless actual test results indicate unsatisfactory performance for the intended application. Flux beyond the warranty may be reconstituted to a working consistency by warming in a water bath and or by additions of distilled or de-ionized warm water.

Flux may require mixing, dilution or warming to regain its normal consistency prior to use. Flux, when placed on a U.S. standard 40 mesh (425 micron) sieve conforming to ASTM E11 and worked lightly with a brush shall pass completely through the sieve. If the flux has partially coagulated in the container, the flux may, before conducting the test, be warmed in a water bath until it has returned to its normal consistency.

### ***AVAILABLE PACKAGING***

---

Handy Flux Liquid is available in a variety of packaging options including Gallon, Quart, and Pint sized containers.

### ***SPECIFICATIONS***

---

Handy Flux Liquid conforms to the following specifications: N/A

### ***APPLICABLE PRODUCT CODE(S)***

---

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 82-055, 36-600, 36-700, and 36-800.

## ***SAFETY INFORMATION***

---

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Handy Flux Liquid.

## ***WARRANTY CLAUSE***

---

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.